

Soda-lime-silica float glass is the most prevalent type of glass used throughout the world for the trade markets. The following table summarizes the thickness and corresponding weight of soda-lime-silica float glass with a density of one hundred fifty-six pounds per cubic foot. This information is offered as a service. Some of the thicknesses listed may not be available from Vitro (formerly PPG Industries). Please check with your Vitro Account Manager for specific product availability.

GLASS THICKNESS AND WEIGHT						
Traditional Designation, (if any)	Millimeters	Range (Inches)	Nominal (Inches)	Weight per Square Foot (Pounds)		
2.0A	2.0	0.069 - 0.088	0.081	1.053		
Picture	2.0	0.071 - 0.084	0.078	1.014		
	2.1	0.080 - 0.088	0.084	1.092		
	2.3	0.085 - 0.093	0.089	1.157		
	2.4	0.091 - 0.098	0.094	1.222		
Single	2.5	0.085 - 0.101	0.089	1.157		
Lami	2.7	0.102 - 0.114	0.108	1.404		
	2.8	0.108 - 0.114	0.111	1.443		
Double or 1/8"	3.0	0.115 - 0.134	0.119	1.547		
	3.1	0.115 - 0.123	0.119	1.547		
DST	3.2	0.121 - 0.129	0.124	1.612		
	3.3	0.125 - 0.133	0.129	1.677		
	3.4	0.131 - 0.137	0.134	1.742		
	3.6	0.136 - 0.142	0.139	1.807		
	3.9	0.150 - 0.157	0.154	2.002		

Vitro Architectural Glass PAGE 1 OF 4



GLASS THICKNESS AND WEIGHT - Continued							
	Weight per						
Traditional Designation, (if any)	Millimeters	eters Range Nomi (Inches) (Inch		Square Foot (Pounds)			
5/32"	4.0	0.150 - 0.164	0.154	2.002			
	4.1	0.156 - 0.164	0.160	2.080			
	4.9	0.185 - 0.193	0.189	2.457			
3/16"	5.0	0.180 - 0.193	0.184	2.392			
	5.5	0.219 - 0.227	0.223	2.899			
1/4"	6.0	0.219 - 0.235	0.223	2.899			
	6.2	0.235 - 0.243	0.239	3.107			
	6.5	0.250 - 0.265	0.258	3.354			
5/16"	5/16" 8.0		0.312	4.056			
	8.1	0.310 - 0.328	0.319	4.147			
	9.6	0.362 - 0.390	0.377	4.901			
3/8"	10.0	0.355 - 0.406	0.377	4.901			
1/2"	12.0	0.469 - 0.531	0.490	6.370			
5/8"	16	0.595 - 0.656	0.613	7.969			
3/4"	19	0.719 - 0.781	0.744	9.672			
7/8"	22	0.844 - 0.906	0.865	11.245			
1"	25	0.969 – 1.031	0.984	12.792			

Note that the "Nominal Glass Thickness" above is used for purposes of general identification and reference in the calculation of the weight only; the actual thickness will be approximately the same as the nominal thickness; however, for at least the reason discussed below, it may not be exactly the same. The formula for calculating the specific weight of soda-lime-silica float glass of an exact thickness is provided below for reference.

Vitro Architectural Glass PAGE 2 OF 4



Float glass manufacturing is a true continuous process. Being a true continuous process, the glass does not stop flowing, even during thickness changes. As a result, float glass is produced utilizing the entire specified thickness range. Any given lite or piece of float glass will typically have a very uniform thickness; however, glass manufacturers will utilize the entire thickness range specified when moving from one thickness of float glass to another. In example, when moving from 6.0mm thickness to 6.2mm thickness, glass will be packed for sale as 6.0mm thickness until the thickness exceeds 0.235". At 0.235" thickness to 0.243" thickness, the glass will be packed as 6.2mm thickness.

When calculating the weight of soda-lime-silica float glass with a density of one hundred fifty-six pounds per cubic foot, of any given thickness, the following formula can be used to determine the weight in pounds, per square foot:

Weight, (pounds) per square foot = 156 lbs/cuft X actual thickness in inches 12 inches/ft

As an additional reference, one can refer to the Dimensional Tolerance Table within the ASTM C1036 Standard Specification for Flat Glass. This and other ASTM standards on glass and glazing are available from ASTM.org.

Vitro Architectural Glass PAGE 3 OF 4



HISTORY TABLE						
ITEM	DATE	DESCRIPTION				
Original Publication	4/15/2002	TD-120				
Revision 1	4/16/2010	Add 3.2mm and Heavy Glass Information and editorial changes to the text and format.				
Revision 2	2016-10-04	Updated to Vitro Logo and format				

This document is intended to inform and assist the reader in the application, use, and maintenance of Vitro Flat Glass products. Actual performance and results can vary depending on the circumstances. Vitro makes no warranty or guarantee as to the results to be obtained from the use of all or any portion of the information provided herein, and hereby disclaims any liability for personal injury, property damage, product insufficiency, or any other damages of any kind or nature arising from the reader's use of the information contained herein.

Vitro Architectural Glass PAGE 4 OF 4