

# Product Data Sheet



## Aesthetic Description

**Solarban® 67** glass by Vitro Architectural Glass (formerly PPG Glass) represents an entirely new vision for transparent, solar control low-e glasses. Its soft, almost undetectable neutral coating endows commercial buildings with a clean, clear appearance that delivers a visual “pop” and the excellent solar control performance architects expect from the **Solarban®** glass family.

Thanks to a proprietary double-silver MSVD coating developed by Vitro, **Solarban® 67** glass transmits and reflects the timbre and brightness of ambient light with true color fidelity. With its clear aesthetic, **Solarban® 67** glass delivers interior and exterior reflectivity of 16 percent and 19 percent, respectively.

## Proven Solar Control Performance

The revolutionary coating enables **Solarban® 67** glass to deliver exceptional levels of solar control performance while delivering a high degree of transparency. In a standard one-inch insulating glass unit (IGU) with conventional clear glass, **Solarban® 67** glass offers a Visible Light Transmittance (VLT) of 54 percent and a Solar Heat Gain Coefficient (SHGC) of 0.29. The result is an impressive Light to Solar Gain (LSG) ratio of 1.86.

In addition to its crisp clarity, **Solarban® 67** glass provides extraordinary performance attributes to help architects meet the increasingly stringent mandates for energy and environmental performance required by contemporary building codes.

Architects desiring even more color and reflectivity options can unite **Solarban® 67** glass in an IGU with clear or tinted glass and with **Vistacool®** subtly reflective or **Solarcool®** traditionally reflective glasses.



**WESTMED Medical Group**

**Location:** Harrison, NY | **Product:** **Solarban® 67** Glass | **Architect:** Design Development, LLC Glass | **Contractor:** E.C. Contracting, Inc. | **Glass Fabricator:** Trulite Glass & Aluminum Solutions

Product*	VLT	SHGC
<b>Solarban® 60</b> Glass (2) Clear	70%	0.39
<b>Solarban® 67</b> Glass (2) Clear	54%	0.29
<b>Solarban® 70XL</b> Glass (2) Clear	64%	0.27

Based on 1-inch IGU with Clear Glass.

With its proprietary neutral double-silver coating, **Solarban® 67** glass provides brilliant transparency along with solar performance that is comparable to triple-silver-coated **Solarban® 70XL** glass.

## Supporting Sustainable Design

Vitro Architectural Glass provides abundant opportunities for architects and building owners to realize their sustainability objectives.

**Energy Use & Operating Cost Reduction:** High-performance glasses by Vitro are engineered to facilitate downsized mechanical equipment costs, leading to reduced long-term energy costs. Visit [tools.vitroglazings.com](http://tools.vitroglazings.com) for glass comparison and configuration tools for analyzing glass products.

**Sustainability Documentation:** Vitro Architectural Glass is the first U.S. float glass manufacturer to have its entire selection of products recognized by the **Cradle to Cradle Certified™** program, and the first in North America to publish third-party verified EPDs for its Flat Glass and Processed Glass products.

For additional credit opportunities and supporting documentation, visit [vitroglazings.com/LEED](http://vitroglazings.com/LEED)

### LEED Credit Opportunities

Possible Points	LEED Credit	<b>Solarban® 67</b> Feature	Path/Option Satisfied
18	Energy & Atmosphere (EA) Optimize Energy Performance	Excellent SHGC, U-value and Tvis performance	Whole Building Energy Simulation (Option 1) or Prescriptive Compliance: ASHRAE Advanced Energy Design Guide (Option 2)
5	Innovation (IN) Innovation in Design	Exceeds minimum performance mandated by local energy codes	Innovation (Option 1), Pilot (Option 2) and Exemplary Performance (Option 3)

Solarban® 67 Glass

Insulating Glass Unit Performance Comparisons   1-inch (25mm) units with 1/2-inch (13mm) airspace and two 1/4-inch (6mm) lites								
Outdoor Lite: Coating if Any (Surface) Glass	Glass Type + Indoor Lite: Coating if Any (Surface) Glass	Visible Light Transmittance (VLT)	Visible Light Reflectance		(BTU/hr <sup>2</sup> ft <sup>2</sup> °F) NFRC U-Value		Solar Heat Gain Coefficient (SHGC)	Light to Solar Gain (LSG)
			Exterior %	Interior %	Winter Nighttime	Winter Argon		
<i>Solarban® 67 Solar Control Low-E Glass</i>								
<i>Solarban® 67 (2) Clear + Clear</i>		54	19	16	0.29	0.24	0.29	1.86
<i>Solarban® 67 (2) Starphire® + Starphire®</i>		57	20	16	0.29	0.24	0.30	1.90
<i>Solarban® 67 (2) Solexia® + Clear</i>		47	16	16	0.29	0.24	0.25	1.88
<i>Solarban® 67 (2) Atlantica® + Clear</i>		41	13	16	0.29	0.24	0.22	1.86
<i>Solarban® 67 (2) Azuria® + Clear</i>		42	13	16	0.29	0.24	0.23	1.83
<i>Solarban® 67 (2) Optiblu® + Clear</i>		39	12	15	0.29	0.24	0.25	1.56
<i>Solarban® 67 (2) Solarblue® + Clear</i>		34	10	15	0.29	0.24	0.22	1.55
<i>Solarban® 67 (2) Pacifica® + Clear</i>		26	8	15	0.29	0.24	0.19	1.37
<i>Solarban® 67 (2) Solarbronze® + Clear</i>		32	10	15	0.29	0.24	0.22	1.45
<i>Solarban® 67 (2) Optigray® + Clear</i>		38	12	15	0.29	0.24	0.24	1.58
<i>Solarban® 67 (2) Solargray® + Clear</i>		27	8	15	0.29	0.24	0.20	1.35
<i>Atlantica® + Solarban® 67 (3) Clear</i>		41	11	18	0.29	0.24	0.29	1.41
<i>Azuria® + Solarban® 67 (3) Clear</i>		42	11	18	0.29	0.24	0.29	1.45
<i>Solarblue® + Solarban® 67 (3) Clear</i>		34	9	18	0.29	0.24	0.30	1.13
<i>Pacifica® + Solarban® 67 (3) Clear</i>		26	7	18	0.29	0.24	0.23	1.13
<i>Solarbronze® + Solarban® 67 (3) Clear</i>		32	9	18	0.29	0.24	0.29	1.10
<i>Optigray® + Solarban® 67 (3) Clear</i>		38	10	18	0.29	0.24	0.32	1.19
<i>Solargray® + Solarban® 67 (3) Clear</i>		27	8	18	0.29	0.24	0.26	1.04
<i>Graylite® II + Solarban® 67 (3) Clear</i>		5	4	18	0.29	0.24	0.12	0.42

**Fabrication and Availability**

Solarban® 67 glass is available exclusively through the Vitro Certified™ Network. Vitro Certified™ Fabricators can meet tight construction deadlines and accelerate the delivery of replacement glass before, during and after construction. Solarban® 67 glass is manufactured using the sputter-coating process and is available for annealed, laminated, heat-strengthened and tempered applications.

**Request Samples**

To obtain samples of any Vitro Glass product, call 1-855-VTRO-GLS (877-6457) or visit [samples.vitroglazings.com](http://samples.vitroglazings.com).



Legacy ER

Location: Allen, TX | Product: Solarban® 67 Optiblu® Glass | Architect: 5G Studio | Contractor: Huffman Builders | Glass Fabricator: Tristars | Glass Contractor: Tepco

For more information about Solarban® 67 low-e glass and other Cradle to Cradle Certified™ architectural glasses by Vitro Glass, visit [vitroglazings.com](http://vitroglazings.com), or call 1-855-VTRO-GLS (887-6457).

©2019 Vitro Architectural Glass. All rights reserved. Solarban, the Solarban logo and Starphire are registered trademarks owned by Vitro. Vitro Certified and the Vitro Certified logo are trademarks owned by Vitro. Cradle to Cradle Certified is a trademark licensed by the Cradle to Cradle Products Innovation Institute. Printed in the USA 09/05/18 (7135)

